

Shademaxx 90% Shadecloth Datasheet

Features	Unit	Result
Facric Detail		
Material		HDPE
GSM		200gsm
Colors		Black, Green, Beige, Charcoal,
		Light Green, Light Grey
Technical		
Warp		
Tensile Strength	N/5cm	>350
Weft		
Tensile Strength	N/5cm	>850
Testing Condition		
Speed Traction	mm/min	200+/-20
Distance between clamps	mm	200
Specimen Width	mm	50
Shade Factor		Black: 97% Green: 90% Charcoal: 85% Light Green: 80% Light Grey: 80% Beige: 73%
Standard Size		1.83 x 30M 3.66 x 30M
Packing		Rolled with paper core with inserts and 2 paper ends then in a clear poly bag